TGS 2442 - for the detection of Carbon Monoxide

Features:

* Low power consumption
* High sensitivity/selectivity to
      carbon monoxide (CO)
* Miniature size
* Low sensitivity to alcohol vapor
* Long life and low cost
* Low humidity dependency

Applications:

* CO detectors
* Air quality controllers
* Indoor parking lot ventilation

TGS 2442 utilizes a multilayer sensor structure. A glass layer for thermal insulation is printed between a ruthenium oxide (RuO_2) heater and an alumina substrate. A pair of Au electrodes for the heater are formed on a thermal insulator. The gas sensing layer, which is formed of tin dioxide (SnO_2), is printed on an electrical insulation layer which covers the heater. A pair of Au electrodes for measuring sensor resistance are formed on the electrical insulator. Activated charcoal is filled between the internal cover and the outer cover for the purpose of reducing the influence of noise gases.

TGS 2442 displays good selectivity to carbon monoxide, making it ideal for CO monitors. In the presence of CO, the sensor's conductivity increases depending on the gas concentration in the air. A simple pulsed electrical circuit operating on a one second circuit voltage cycle can convert the change in conductivity to an output signal which corresponds to gas concentration.

The figure below represents typical sensitivity characteristics, all data having been gathered at standard test conditions (see reverse side of this sheet). The Y-axis is indicated as sensor resistance ratio (Rs/Ro) which is defined as follows:

Rs = Sensor resistance of displayed gases at various concentrations
Ro = Sensor resistance in 100ppm CO

The figure below represents typical temperature and humidity dependency characteristics. Again, the Y-axis is indicated as sensor resistance ratio (Rs/Ro), defined as follows:

Rs = Sensor resistance at 30ppm, 100ppm and 300ppm of CO at various temperatures and 50%R.H.
Ro = Sensor resistance at 300ppm of CO at 25°C and 50% R.H.

Sensitivity Characteristics:


Temperature/Humidity Dependency:

深圳市新世联科技有限公司

Basic Measuring Circuit:

Circuit voltage (Vc) is applied across the sensing element which has a resistance (Rs) between the sensor's two electrodes (pins No. 2 and No. 3) and a load resistor (RL) connected in series. The sensing element is heated by the heater which is connected to pins No. 1 and No. 4.

Heating cycle--The sensor requires application of a 1 second heating cycle which is used in connection with a circuit voltage cycle of 1 second. Each VH cycle is comprised by 4.8V being applied to the heater for the first 14ms, followed by 0V pulse for the remaining 986ms. The Vc cycle consists of 0V applied for 995ms, followed by 5.0V for 5ms. For achieving optimal sensing characteristics, the sensor's signal should be measured after the midpoint of the 5ms Vc pulse of 5.0V (for reference, see timing chart below).

NOTE: Application of a Vc pulse condition is required to prevent possible migration of heater materials into the sensing element material. Under extreme conditions of high humidity and temperature, a constant Vc condition could result in such migration and cause long term drift of Rs to higher values. A 5ms Vc pulse results in significantly less driving force for migration than a constant Vc condition, rendering the possibility of migration negligibly small.

Structure and Dimensions:

unit: mm

Top View

Side View

Bottom View

unit;mm

Specifications:

Model number			TGS 2442
Sensing element type			M1
Standard package			TO-5 metal can
Target gases			Carbon monoxide
Typical detection range			30 ~ 1000 ppm
Standard circuit conditions	Heater voltage cycle	V_H	V_{HH}=4.8V±0.2V DC, 14ms V_{HL}=0.0, 986ms
	Circuit voltage cycle	V_C	V_C=0V for 995ms, V_C=5.0V±0.2V DC for 5ms
	Load resistance	R_L	variable (≥10kΩ)
Electrical characteristics under standard test conditions	Heater resistance	R_H	17 ± 2.5Ω at room temp.
	Heater current	I_H	approx. 203mA(in case of V_{HH})
	Heater power consumption	P_H	approx. 14mW (ave.)
	Sensor resistance	R_s	13.3kΩ ~ 133kΩ in 100ppm of carbon monoxide
	Sensitivity (change ratio of Rs)	β	0.13 ~ 0.31
Standard test conditions	Test gas conditions		Carbon monoxide in air at 20±2°C, 65±5%RH
	Circuit conditions		Same as Std. Circuit Condition (above)
	Conditioning period before test		2 days or more

Sensor resistance (Rs) is calculated with a measured value of Vout as follows:

$$Rs = \frac{Vc \times RL}{Vout} - RL$$

The value of sensitivity (β) is calculated with two measured values of Rs as follows:

$$\beta = \frac{Rs\ (CO,300ppm)}{Rs\ (CO,100ppm)}$$

深 圳 市 新 世 联 科 技 有 限 公 司